

PROPERTIES		TEST METHOD	VALUES
Filament blend			PET/PA
Web bonding		EN 29092	hydrolace
Mass per unit area	g/m ²	EN 9073-1	target 200
Thickness	mm	ISO 9073-2	target 0,75
Tensile strength Machine direction	N	EN 13934-1	target 620
Tensile strength Cross direction	N	EN 13934-1	target 700
Tear strength Machine direction	N	EN 13 937	target 40
Tear strength Cross direction	N	EN 13 937	target 40
Elongation at break Machine direction	%	EN 13934-1	target 55
Elongation at break Cross direction	%	EN 13934-1	target 60
Surface resistivity	Ohms	EN 100 015/1	target 109

Technical data on this data sheet refer to non-binding reference samples only. Binding specifications will be agreed separately. The customer is responsible for conducting his/her own tests to determine for him/herself the suitability of the products for his/her particular purposes. The customer is especially responsible for testing the suitability of the product for specific post-treatments before large-scale production.