

EVO 240 SG 110SP AS
ReinforcedwithSpunbondnon-woven



Data Sheet



EVOLON

Filament blend	(DIN 60000-T01)	PES / PA 6
Color of the surface web		GREY
Evolon (both layers) weight	(EN 964-1)	130 g/m²

REINFORCEMENT

Web composition	(DIN 60000-T01)	PES
Web weight	(EN 964-1)	110 g/m²

COMPOSITE

Web bonding	(EN 29092)	hydrolace
Mass per unit area	(EN 964-1)	240 g/m²
Standard width		1600 mm
Thickness	(EN 13934-1)	1,00 mm
Tensile strength (md)	(EN 13934-1)	800 N
Tensile strength (cd)	(EN 13934-1)	600 N
Elongation at break (md)	(EN 13934-1)	50%
Elongation at break (cd)	(EN 13934-1)	50%
Tear resistance (md)	(EN 13937)	40 N
Tear resistance (cd)	(EN 13937)	45 N
Surface Resistivity after 2 hours in a climate room	ASTM D-257	107 - 108 Ohm2

Roll make-up	Core diameter	76 mm
	Max. diameter	600 mm
	Standard length	ap. 300 mts
	Wrapping	Individual foil

Average values, subject to normal production tolerances.

