

Determination	Method	Result	
Polymer	PVC coated	Conductive PVC	
Surface resistivity	EN 1149-1	1	1.54×10^{E3}
		2	1.24×10^{E3}
		3	1.09×10^{E3}
Surface resistivity	EN 1149-3	Measurement	90% decay time t_{90} (s)
		1	<0.01
		2	<0.01
		3	<0.01
Weight	ISO 536	630gsm	
Thickness	EN 20534	170 μm	
Breaking strength	EN ISO 13934	MD 1500N / CD 1500N	
Tearing strength	ISO 9073	MD 220N / CD 180N	
Elongation at break	EN ISO 13934	20%	